

Features	Test Method	Value		
Surface Quality	ISO 10545-2	> 95%		
Curvature Flatness		± 0.5 % / ± 2.0 mm		
Thickness		± 5% / ± 0.5 mm		
Length and Width		± 0.6 % / ± 2.0 mm		
Rectangularity		± 0.5% / ± 2.0 mm		
Straightness of Sides		± 0.5 % / ± 1.5 mm		
Water Absorption	ISO 10545-3	< 0.5 %		
Breaking Strength	ISO 10545-4	> 1300 N		
Modulus of Rupture	ISO 10545-4	> 35 N/mm ²		
Surface Abrasion Resistance	ISO 10545-7	2 (Aubergine) 3 (White Sage)		
Visible Failure at No. of Revolutions	ISO 10545-7	600 Rev (Aubergine) 750 Rev (White Sage)		
Surface Scratch Resistance	EN-101	5		
Thermal Shock Resistance	ISO 10545-9	Resistant		
Crazing Resistance	ISO 10545-11	Resistant		
Frost Resistance	ISO 10545-12	Resistant		
Chemical Resistance	ISO 10545-13	High	Low	Household
		HA	LA	A
Stain Resistance	ISO 10545-14	5/-/5/5		
Critical Angle (Footwear)	DIN-51130	R-9		
Slip Resistance (Pendulum Test)	UNE-ENV-12633	1		
DCOF (WET)	ANSI A137.1	> 0.42		
Recycled Material	-	≥39.9%		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Glossy/Matte Finish
- 8.5mm Thickness
- Pressed Edge
- PEI Rating = 2 (Aubergine)
3 (White | Sage)
- V1 - Uniform Appearance
- Frost Resistance = Yes

