

Features	Test Method	Value
Water Absorption	ASTM C373-18	≤ 0.5
Abrasion Resistance	ASTM C1027-19	4
Scratch Hardness (MOHS)	-	4
Breaking Strength	ASTM C648-04	275
Chemical Resistance	ASTM C650-04	Class A
Frost Resistance	ASTM C1026	Resistant
Stain Resistance	ASTM C1378-04	Class B
DCOF (WET)	ANSI A326.6	≥0.42
Recycled Material	-	4%

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Matte | Polished Finishes
- 8mm Thickness
- Rectified | Pressed Edge
- PEI Rating = 4
- V3 - Moderate Variation
- Frost Resistance = Yes



Features	Test Method	Value
Water Absorption	ASTM C373-18	$7.0 \leq x < 20.0$
Scratch Hardness	-	3
Breaking Strength	ASTM C648-04	125
Chemical Resistance	ASTM C650-04	Class A
Stain Resistance	ASTM C1378-04	Class A
Frost Resistance	ASTM C1026	Not Resistant
Recycled Material	-	14%

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- 8mm Thickness
- Pressed Edge
- V3 - Moderate Variation
- Frost Resistance = No