

Features	Test Method	Value		
Length and Width	ISO 10545-2	±0.1%		
Thickness	ISO 10545-2	10.4 ± 3.0 %		
Straightness of Sides	ISO 10545-2	±0.1%		
Rectangularity	ISO 10545-2	±0.1%		
Water Absorption	ISO 10545-3	14%		
Breaking Strength	ISO 10545-4	1200 N		
Modulus of Rupture	ISO 10545-4	25 N/mm²		
Coefficient of Linear Thermal Expansion	ISO 10545-8	7.3 x 10 <sup>-6</sup>		
Thermal Shock Resistance	ISO 10545-9	Resistant		
Crazing Resistance	ISO 10545-11	Resistant		
Chemical Resistance	ISO 10545-13	Household Chemicals GA	Low Concentration GLA	High Concentration GHA
Stain Resistance	ISO 10545-14	5		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

## **Product Info:**

- Ceramic Wall Tile
- Matte Finish
- 10.4mm Thickness
- Rectified Edge
- V2 Slight Shading Variation
- Frost Resistance = No



www.genrose.com