

Features	Test Method	Value		
Length and Width	ISO 10545-2	$\pm 0.3 \%$		
Thickness	ISO 10545-2	$10 \pm 3.0 \%$		
Straightness of Sides	ISO 10545-2	$\pm 0.3 \%$		
Rectangularity	ISO 10545-2	$\pm 0.3 \%$		
Surface Flatness	ISO 10545-2	$\pm 0.2 \%$		
Water Absorption	ISO 10545-3	$\leq 0.5\%$		
Breaking Strength	ISO 10545-4	$>1300 \text{ N}$		
Modulus of Rupture	ISO 10545-4	$>35 \text{ N/mm}^2$		
Thermal Shock Resistance	ISO 10545-9	Resistant		
Crazing Resistance	ISO 10545-11	Resistant		
Frost Resistance	ISO 10545-12	Resistant		
Coefficient of Friction	-	R10		
Chemical Resistance	ISO 10545-13	Household	Low Conc.	High Conc.
		GA	GLA	GHA
Resistance to Stains	ISO 10545-14	5		
D.C.O.F. (WET) Slip Resistance	ANSI A326.3	0.62		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Disclaimer: DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

Product Info:

- Color Body Porcelain Tile
- Matte Finish
- 10mm Thickness
- Pressed Edge
- V2 - Slight Shading Variation
- Frost Resistance = Yes


www.genrose.com