

Features	Test Method	Value
<b>Water Absorption</b>	ISO 10545-3	≤ 0.5
<b>Breaking Strength</b>	ISO 10545-4	> 1300 N
<b>Bending Strength</b>	ISO 10545-4	> 35 N/mm <sup>2</sup>
<b>Surface Abrasion</b>	ISO 10545-7	4 (White   Natural   Gray) 3 (Miel)
<b>Cracking Resistance</b>	ISO 10545-11	Resistant
<b>Frost Resistance</b>	ISO 10545-12	Resistant
<b>Chemical Resistance</b>	ISO 10545-13	Minimum GB
<b>Resistance to Acid and Alkaline</b>	ISO 10545-13	GHA
<b>Resistance to Stains</b>	ISO 10545-14	Minimum Class 3
<b>DCOF (WET)</b>	ANSI A137. 1:2012. 9.6	> 0.42
<b>Hardness (MOHS)</b>	EN 101	Minimum 3

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Glazed Porcelain Tile
- Matte Finish
- 9.7mm Thickness
- Rectified Edge
- PEI Rating = 4 (White | Natural | Gray)  
3 (Miel)
- V3 - Moderate Variation
- Frost Resistance = Yes

