

Features	Test Method	Value	
Dimensions and Appearance	ISO 10545-2	Prospect L1	
Water Absorption	ISO 10545-3	> 10%	
Flexural Resistance	ISO 10545-4	17 N/mm ²	
Modules of Rupture		< 7.5 mm	≥ 7.5 mm
		200 N	600 N
Coefficient of Linear Thermal Expansion	ISO 10545-8	≤ 7x10 ⁻⁶ °C ⁻¹	
Resistance to Sudden Temperature Changes	ISO 10545-9	Resistant	
Crazing Resistance	ISO 10545-11	Resistant	
Resistance to Household Chemicals and Swimming Pool Cleansers	ISO 10545-13	min. GB	
Stain Resistance	ISO 10545-14	min. 3	

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- 9.8mm Thickness
- V2 - Slight Shading Variation
- Frost Resistance = No

