

Features	Test Method	Value
<b>Dimensions</b>	ISO 10545-2:97	±0.8mm
<b>Surface Flatness</b>	ISO 10545-2:97	<0.3%
<b>Water Absorption</b>	ISO 10545-3:97	<0.5%
<b>Breaking Strength</b>	ISO 10545-4	>35 N/mm <sup>2</sup>
<b>Abrasion Resistance</b>	ISO 10545-7:99	4 (Black) 5 (All Other Tiles)
<b>Crack Resistance</b>	ISO 10545-11:97	Resistant
<b>Frost Resistance</b>	ISO 10545-12:97	Resistant
<b>Chemical Resistance</b>	ISO 10545-13:1998	GLA
<b>Stain Resistance</b>	ISO 10545-14:98	5
<b>Slip Resistance</b>	ANSI A326.3 DCOF	>0.42

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Disclaimer:** DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

**Product Info:**

- Glazed Porcelain Tile
- Matte Finish
- 8.3mm Thickness
- Pressed Edge
- PEI Rating = 4 (Black) | 5 (All Other Tiles)
- V1 - Uniform Variation
- Frost Resistance = Yes



[www.genrose.com](http://www.genrose.com)