

Features	Test Methods	Value Required	Our Value
Length and Width	ISO 10545-2	± 0,5%	± 0,5%
Thickness		± 10%	± 5%
Straightness of Edges		± 0,3%	± 0,3%
Wedging		± 0,5%	± 0,4%
Warpage		± 0,5%	± 0,3%
Water Absorption	ISO 10545-3	E>10%	~16%
Bending Strength	ISO 10545-4	R≥15 N/mm ²	22 N/mm ²
Abrasion Resistance	ISO 10545-7	According to the manufacturer's data	Indicated in the catalog
Coefficient of Linear Thermal Expansion	ISO 10545-8	Test Method Available	8x10 ⁻⁶ °C ⁻¹
Thermal Shocks Resistant	ISO 10545-9	Test Method Available	Comply
Crazing Resistance	ISO 10545-11	Test Method Available	Comply
Chemical Resistance	ISO 10545-13	Minimum GB	Comply
Stain Resistance	ISO 10545-14	Minimum Class 3	Comply

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy Finish
- Frost Resistance = No
- Contact your sales representative for more information

