

Features	Test Method	Value
Length and Width	UNI-EN ISO 10545-2	± 0.5%
Thickness	UNI-EN ISO 10545-2	± 10%
Straightness of Sides	UNI-EN ISO 10545-2	± 0.3%
Rectangularity	UNI-EN ISO 10545-2	± 0.5%
Surface Flatness - Centre Curvature	UNI-EN ISO 10545-2	± 0.5% - 0.3%
Surface Flatness - Side Curvature	UNI-EN ISO 10545-2	± 0.5% - 0.3%
Surface Flatness - Warping	UNI-EN ISO 10545-2	± 0.5%
Breaking of Rupture	UNI-EN ISO 10545-4	> 600 N (≥ 7.5 MM) > 200 N (< 7.5 MM)
Modulus of Rupture	UNI-EN ISO 10545-4	> 12 N/MM ² (≥ 7.5 MM) > 15 N/MM ² (< 7.5 MM)
Scratch Resistance (MOHS)	EN-101	3*
Water Absorption	UNI-EN ISO 10545-3	> 10 %
Color Resistance to Light	DIN 51094	Resistant
Linear Thermal Expansion Coefficient(100°C)	UNI-EN ISO 10545-8	Test Method Available
Thermal Shock Resistance	UNI-EN ISO 10545-9	Resistant*
Resistance to Stains	UNI-EN ISO 10545-14	Class 5*
Chemical Resistance	UNI-EN ISO 10545-13	GB Min.
Lead and Cadmium Given Off	UNI-EN ISO 10545-15	Test Method Available
Reaction to Fire	EN 13501-1	A1

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

*Excluding Metallic Colors (Oro, Bronzo, Acciaio)

Product Info:

- Ceramic Tile
- Glossy | Metal Finishes
- 9mm Thickness
- Pressed Edge
- V2 (Bianco) | V3 (All Other Colors)
- Frost Resistance = No


www.genrose.com