

Features	Test Method	Value	
<b>Water Absorption</b>	ISO 10545-3	14.95%	
<b>Frost Resistance</b>	ISO 10545-12	Not Resistant	
<b>Surface Hardness</b>	EN 101	3	
<b>Cracking Resistance</b>	ISO 10545-11	OK	
<b>Chemical Resistance</b>	ISO 10545-13	-	
<b>Sodium Hxipochloride</b>		GA	
<b>Hydrochloric Acid - 3%</b>		GLA	
<b>Citric Acid - 100 g/l</b>		GLA	
<b>Potasic Hydroxide - 30 g/l</b>		GLA	
<b>Hydrochloric Acid - 18%</b>		GHB	
<b>Lactic Acid - 5%</b>		GHA	
<b>Potasic Hydroxide - 100 g/l</b>		GHA	
<b>Fire Resistance</b>		EN 13501-1	A1

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Ceramic Tile
- Matte Finish
- Pressed Edge
- Frost Resistance = No

