



Features	Test Method	Value		
Reaction to Fire	Decision 96/603/CEE as amended	A1 _{fl}		
Water Absorption	ISO 10545-3	≤0.5%		
Bending Strength	ISO 10545-4	S >700 N for thickness < 7,5 mm R >35 N/mm ² for thickness < 7,5 mm S >1300 N for thickness ≥ 7,5 mm R >35 N/mm ² for thickness ≥ 7,5 mm		
Thermal Shock Resistance	ISO 10545-9	Resistant		
Frost Resistance	ISO 10545-12	Resistant		
Resistance of Chemical Attack	ISO 10545-13	High Concentration	Low Concentration	Domestic Chemicals
		Resistant	Resistant	Compliant
Stain Resistance	ISO 10545-14	Class 5		