

Features	Test Method	Value
Length and Width	ISO 10545-2	$\pm 0.6\% \pm 2.0\text{mm}$
Thickness		$\pm 5\% \pm 0.5 \text{ mm}$
Straightness of Sides		$\pm 0.5\% \pm 1.5 \text{ mm}$
Rectangularity		$\pm 0.5\% \pm 2.0 \text{ mm}$
Surface Flatness		$\pm 0.5\% \pm 2.0 \text{ mm}$
Water Absorption	ISO 10545-3	< 0.5%
Breaking of Rupture	ISO 10545-4	> 1300 N
Modulus of Rupture		> 35 N/mm ²
Surface Abrasion Resistance	ISO 10545-7	4
Scratch Hardness	EN 101	7
Coefficient of Linear Thermal Expansion	ISO 10545-8	$6.5 \times 10^{-6} \text{ }^{\circ}\text{C}$
Thermal Shock Resistance	ISO 10545-9	Guaranteed
Crazing Resistance	ISO 10545-11	Guaranteed
Frost Resistance	ISO 10545-12	Guaranteed
Chemical Resistance to Low Concentrations of Acids and Alkalis	ISO 10545-13	GLA
Chemical Resistance to High Concentrations of Acids and Alkalis		GHA
Chemical Resistance to Household Chemicals		GA
DCOF (WET)	ASTM BOT3000	≥ 0.42
Stain Resistance	ISO 10545-14	5
Recycled Content	-	Min. 24%

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Matte Finish
- 9mm Thickness
- Pressed Edge
- PEI Rating = 4
- V2 - Slight Shading Variation
- Frost Resistance = Yes

