

Features	Test Method	Value
<b>Length and Width</b>	ISO 10545-2	701.0 ± 0.60 mm 249.8 ± 0.40 mm
<b>Thickness</b>		10.10 ± 0.50 mm
<b>Straightness of Sides</b>		≤ 0.60 mm
<b>Squareness</b>		≤ 0.80 mm
<b>Surface Flatness</b>		+ 0.90 mm / - 0.50 mm
<b>Breaking Strength</b>	ISO 1054-4	900 N
<b>Modulus of Rupture</b>		19 N/mm <sup>2</sup>
<b>Staining Resistance</b>	ISO 10545-14	Class 5
<b>Chemical Resistance</b>	-	GA/ GLA/ GHA
<b>Fixing</b>	UNE CEN/TR 12548 IN	Min: in 2.5 mm

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Ceramic Tile
- Matte Finish
- Pressed Edge
- V3 - Moderate Variation
- Frost Resistance = No


[www.genrose.com](http://www.genrose.com)