


Features	Test Method	Value
Dimensions	ISO 10545 - 2	Compliant
Surface Quality		Min. 95% of tiles free of visible defects
Water Absorption	ISO 10545 - 3	0%
Thermal Shock Resistance	ISO 10545 - 9	Resistant
Crazing Resistance	ISO 10545 - 11	Resistant
Chemical Resistance (Domestic)	ISO 10545 - 13	GA
Chemical Resistance (Low Concentration)		GLA
Chemical Resistance (High Concentration)		GHA
Fire Resistance	-	A1/A1 <sub>FL</sub>
Slip Resistance (Wet)	ANSI A137.1	DCOF 0.69
Recycled Content	-	100%
VOC Emissions	-	Zero VOC
		

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Disclaimer:** DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

**Product Info:**

- Glass Tile
- Matte Finish
- 5.5mm | 5.6mm Thicknesses
- Pressed Edge
- V3 - Moderate Variation
- Frost Resistance - Yes


[www.genrose.com](http://www.genrose.com)