

Features	Test Method	Value
Length and Width	ASTM C499	± 2.0% of nominal dimensions
Thickness		≤ 0.031"
Straightness of Sides		± 0.40% or max ± 0.05"
Rectangularity		± .25%
Surface Flatness		± 0.40% or max ± 0.05"
Warpage	ASTM C485	- .30% / + .40% or max - 0.05"/+0.07"
Wedging	ASTM C502	±.40% or max ±.05"
Water Absorption	ISO 10545-3	<10%
Modulus of Rupture / Bending Strength	ISO 10545-4	≥ 15 N/mm ²
Breaking Strength	ISO 10545-4	≥ 200 N
Abrasion Resistance	ISO 10545-8	7.1x10 ⁻⁶ C ⁻¹
Coefficient of Linear Thermal Expansion	ISO 10545-9	Compliant
Thermal Shock Resistance	ISO 10545-11	Resistant
Crazing Resistance	ISO 10545-12	Resistant
Frost Resistance	ASTM 1026	Not Resistant
Chemical Resistance	ASTM C650	LA, HA
Stain Resistance	ASTM C1378	Resistant
Recycled Material	-	62%
VOC Emissions		Zero VOC

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Glossy | Matte Finishes
- 9mm | 15mm Thicknesses
- Pressed Edge
- V1 - Uniformed Variation
- Frost Resistance = No

Note:

Product is subject to natural shade variation when mixing textures and sizes.



www.genrose.com