

Features	Test Method	Value	
Dimensions	ISO 10545-2	Various	
		Length	Width
From Work Sizes	ISO 10545-2	0.00%. 0.0mm / 0.12%. 0.3mm	-0.12%. -0.1mm / 0.37%. 0.3mm
Straightness	ISO 10545-2	-0.04%. -0.1mm / 0.04%. 0.1mm	0.00%. 0.0mm / 0.00%. 0.0mm
Rectangularity	ISO 10545-2	-0.16%. -0.4mm / 0.16%. 0.4mm	-0.12%. -0.1mm / 0.12%. 0.1mm
Edge Curvature	ISO 10545-2	-0.20%. -0.5mm / 0.00%. 0.0mm	0.00%. 0.0mm / 0.00%. 0.0mm
Center Curvature	ISO 10545-2	-0.19%. -0.5mm / 0.00%. 0.0mm	
Warpage	ISO 10545-2	-0.04%. -0.1mm / 0.04%. 0.1mm	
Thickness	ISO 10545-2	0.00%. 0.0mm / 1.25%. 0.1mm	
Surface Quality	ISO 10545-2	100%	
Water Absorption	ISO 10545-3	E= 18.0% min 17.3%	
Breaking Strength	ISO 10545-4	860N	
Modulus Of Rupture	ISO 10545-4	e ≥ 7.5mm	
		Min=19 N/mm ² Media=21 N/mm ²	
Thermal Coefficient of Linear Expansion	ISO 10545-8	5.9 x 10 ⁻⁶ °K ⁻¹	
Thermal Shock Resistance	ISO 10545-9	Resistant	
Crazing Resistance	ISO 10545-11	Resistant	
Resistance of Chemical Attack	ISO 10545-13	Low Concentration	Domestic Chemicals
		GLA	GA
Stain Resistance	ISO 10545-14	Class 5	

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Matte | Glossy Finishes
- 8mm Thickness
- Pressed Edge
- V2 - Slight Shading Variation
- Frost Resistance = No


www.genrose.com