

Features	Norms	Fixed Value
Facial Defects	ANSI A 137.2 7.1	Complied
Structural Defects	ANSI A 137.2 7.1	Complied
Thickness	ASTM C499	.43mm
Nominal Size	ASTM C499	-2.54%~-0.04%
Caliber Range	ASTM C499	-1.10%~+1.14%
Static Coefficient of Friction	ASTM C1028	Dry: 0.83 Wet: 0.61
Dynamic Coefficient of Friction	Refer to ASTM C1028	Dry: 0.60 Wet: 0.55
Water Absorption	ASTM C373	0.03%~0.05%
Chemical Resistance	ASTM C650	Not affected
Chemical Resistance Class	ANSI A 137.2 5.2.3.5	Class A
Stain Resistance	ASTM C1378	Not affected
Stain Resistance Class	ANSI A 137.2 5.2.3.6	Class A
Linear Thermal Expansion	ASTM C372	N/A
Moisture Expansion	ASTM C370	N/A
Thermal Shock Resistance	ANSI A 137.2 7.9	Resistant
Frost Resistance	ASTM C1026	Resistant

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Enamel Glass Mosaic
- Matte | Gloss Finishes
- 9.5mm Thickness
- Frost Resistance = Yes



www.genrose.com

Features	Norms	Fixed Value
Break Strength	ASTM C648-04 - ANSI A 137.1	521 lbf
Chemical Resistance Class	ANSI A137.1/A137.2	Class A

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Ceramic Tile
- Gloss Finish
- 9.5mm Thickness
- PEI = 5 - Heavy Commercial (Snow in Gloss Finish Only)
Wall and Light Duty Floors (Light Colors in Gloss Finish)
(Dark Colors will show scuffs if placed on floor)
- Frost Resistance = No

