

Features	Test Method	Value
<b>Dimensional Features</b>	ISO 10545-2	62 mm +/- 0.75 mm x 125 mm +/- 0.75 mm
<b>Water Absorption</b>	ISO 10545-3	$E_b \leq 10\%$
<b>Modulus of Rupture</b>	ISO 10545-4	Thickness $\geq 7.5$ mm Min 12 N/mm <sup>2</sup> Thickness $< 7.5$ mm Min 15 N/mm <sup>2</sup>
<b>Crazing Resistance</b>	ISO 10545-11	Resistant
<b>Household Chemical Resistance</b>	ISO 10545-13	GA
<b>Chemical Resistance</b>	ISO 10545-13	GHA (except for Steel and Copper)
<b>Stain Resistance</b>	ISO 10545-14	5

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

**Product Info:**

- Ceramic Tile
- Matte | Glossy Finish
- 10mm Thickness
- Pressed Edge
- V4 - Substantial Variation
- Frost Resistance = No


[www.genrose.com](http://www.genrose.com)