

Features	Test Method	Value	
Length and Width	ISO 10545-2	± 0.5% ± 2mm	
Thickness		± 5% ± 0.5mm	
Straightness of Sides		± 0.3% ± 1.5mm	
Rectangularity		± 0.3% ± 1.5mm	
Surface Flatness		± 0.3% ± 1.5mm	
Water Absorption	ISO 10545-3	E ≤ 0.1% Bla GL	
Modulus of Rupture	ISO 10545-4	R ≥ 35 N/mm ²	
Breaking of Rupture		S ≥ 1300 N	
Abrasion Resistance	ISO 10545-7	Class 4	
Crazing Resistance	ISO 10545-11	Resistant	
Frost Resistance	ISO 10545-12	Resistant	
Resistance to Household Chemicals	ISO 10545-13	Class A-LA	
Resistance to Low Concentrations of Acids and Bases			
Stain Resistance	ISO 10545-14	Class 5	
Scratch Hardness (Mohs)	EN 101	Matte: ≥ 6 Polished: ≥ 5	
Slip Resistance		Matte	Polished
	DIN 51130	R10	-
	B.C.R.A. REP. CEC. 6/81	0.40 ≤ ≤ 0.74	-
	DIN 51097	Class C	Class B
	DCOF Acu Test	WET > 0.42	-

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Matte | Polished Finish
- 10mm Thicknesses
- Rectified Edge
- PEI Rating = 4
- V2 - Slight Shading Variation
- Frost Resistance = Yes

