

Features	Test Method	Value
Length and Width	ISO 10545-2	$\pm 0.5\% \pm 2 \text{ mm}$
Thickness		$\pm 5\% \pm 0.5 \text{ mm}$
Straightness of Sides		$\pm 0.3\% \pm 1.5 \text{ mm}$
Rectangularity		$\pm 0.3\% \pm 1.5 \text{ mm}$
Surface Flatness		$\pm 0.3\% \pm 1.5 \text{ mm}$
Water Absorption	ISO 10545-3	$E \leq 0.3\% \text{ Bla GL}$
Frost Resistance	ISO 10545-12	Resistant
Thermal Shock Resistance	ISO 10545-9	Resistant
Crazing Resistance	ISO 10545-11	Resistant
Scratch Hardness	-	> 6
Surface Abrasion Resistance	ISO 10545-7	Class 4-5
Resistance to Household Chemicals	ISO 10545-13	Class A
Resistance to Low Concentrations of Acids and Alkalis		Class LA
Stain Resistance	ISO 10545-14	Class 5
Bending Strength	ISO 10545-4	$R \geq 35 \text{ N/mm}^2$
DCOF	-	> 0.42

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Product Info:

- Glazed Porcelain Tile
- Matte Finish
- 10mm Thickness
- Pressed Edge
- V3 - Moderate Variation
- Frost Resistance = Yes


www.genrose.com