GENROSE

TWIRL

Glazed Porcelain Tile

Features	Test Method	Value
Thickness	ASTM C499	± 0.03"
Surface Quality		Min. 95% of tiles free of visible defects
Warpage	ASTM C485	Compliant
Wedging	ASTM C502	Compliant
Water Absorption	ASTM C373	≤ 0.5%
Breaking Strength	ASTM C648	≥ 250 lbf
Coefficient of Linear Thermal Expansion	ASTM C372	Compliant
Thermal Shock Resistance	ASTM C484	Resistant
Crazing Resistance	ASTM C424	Resistant
Chemical Resistance (Domestic)	ASTM C650	Not Affected
Fire Resistance	-	$A1/A1_{FL}$
Slip Resistance (Wet)	ANSI A326.3	DCOF 0.76
LEED	-	Yes
Recycled Content	-	0%
VOC Emissions	-	Zero VOC
Greenguard	-	Greenguard Gold

This product will contribute to USGBC registered LEED projects.
It will also contribute to the ANSI approved NAHB Green Building Standard ICC 700.

According to ANSI and MIA standards, depending on the type and size of tile, it is recommended to have at least a 1/8" wide grout joint for floor tiles in order to be able to fill the grout joint full and never less than 1/16" wide. Please refer to TCNA guidelines for more on grout recommendations.

Disclaimer: DCOF wet and dry is different on every production lot and can vary. This number represents the average DCOF of the tested production lots. If the spec listed is over the minimum standard, it will meet the requirement.

Product Info:

- Glazed Porcelain Tile
- Matte Finish
- 8mm Thickness
- Pressed Edge
- V3 - Moderate Variation
- Frost Resistant

www.genrose.com